



## Technical Data Sheet

### PVC Stabilizer

Code: CWCS-606

#### **Description:**

We choose superfine Di/Tri-basic salt, Reasonable collocate with many kinds of high

Effective internal and external lubricant, Compound it with advanced craft and technology.

The product has excellent thermal stability, plasticizing fast, good fluidity, etc. Reasonable and effective Mixing proportion of lubricants, makes this model has wider range of processing, applicable for various processing equipment and technology, processing

Performance is excellent. This product uses a more reasonable production craft, the final form is flake, belongs to Dust-free products. hot mix temperature is 105-115°C.

#### **Specification:**

Appearance:	white or light yellow flake
Lead content:	36.0 ± 1.0%
Density :	0.45 g/cm <sup>3</sup>

#### **Area of Application:**

PVC profile, window profiles, door profiles

#### **Recommended Mix:**

Depending on method of production and formulation

#### **Packing Details:**

25 KG/bag, normal temperature drying storage

www.caspian-polymer.com

E-mail : info@caspian-polymer.com | Hafez St, Dehkhoda Blvd, Caspian Industrial Town, Qazvin-IRAN  
Sales : marketing@caspian-polymer.com | Tel : (+98) 283 284 81 50 - 2 Fax : (+98) 283 284 81 53  
Management : Management@caspian-polymer.com